

Data för artikel: 1841305 Glasfibernät 6x6mm 1,0x50 m

		Tolerance +/-			
Loomstate weight	(g/m ²)	129		5%	DIN 53854
Finished weight	(g/m ²)	160		5%	DIN 53854
Coating	(g/m ²)	31		5%	
Coating	(%)	24		5%	DIN ISO 1887
Width	(cm)	100		0,5	
		warp	weft		
Aperture size	(mmxmm)	6,8	6,4	0,2	
Yarn count	(yarns/10 cm)	13,5	12	0,5	DIN 53854
Tensile strength	(N/5 cm)	1800	1850	∅	DIN 53857T1
Elongation	(%)	3,25	3,5	max.	

Data för artikel: 1841012 Glasfibernät 10x12mm 1,0x50 m

		Tolerance +/-			
Finished weight	(g/m ²)	165		5%	DIN EN 12127
Coating	(g/m ²)	32		5%	DIN EN 12127
		warp	weft		
Aperture size	(mmxmm)	9	9,5	0,2	
Yarn count	(yarns/10 cm)	10	8,5	0,5	DIN EN 12127
Tensile strength	(N/5 cm)				
Original strength		2000	2500	∅	DIN EN ISO 13934-1
Elongation	(%)	3,5	4,1		
Coating type		SBR-Latex			
Weave		Leno			DIN 61101-1 + DIN ISO 9354
Standard measurement	(cmxm)	100	50		